

CERTIFICATE OF ANALYSIS

17 OCT 2018

Material Description: Eastoflex(TM) E1003 Amorphous Polyolefin, Bulk
Customer Order :
Outbound Delivery :
Shipper Sales Order :
Ship Date : 17 OCT 2018
Batch / Lot :
Cust.Material No :
Vehicle No :
Net Weight, LB : 41,419.990

Characteristic	Results	Shipping	
		Lower	Upper
Production Date	10/16/2018		
Viscosity @ 190C, CPS	256	150	350
Softening Point, °C	123.1	115.0	130.0
Color, Gardnr	1.0		2.0
Penetration, dmm	109.2		

Storage - Inside storage is recommended. Flaked, pelletized or pastillated forms of this product may remass under the following conditions:

- * If stored near sources of heat
- * Upon prolonged storage above 30 deg C (86 deg F)
- * With pressure (e.g., stacking pallets two or more high)

Remassing has no influence on the physical properties of the finished product. However, it is strongly recommended that strict control of stored inventory be observed at all times, taking care that the oldest material is used first.

For questions regarding this document call 1-800-EASTMAN.



Roger C. Kenton, Team Leader # Quality Assurance
Chemical and Environmental Laboratory