

CERTIFICATE OF ANALYSIS (EN10204 3.1)

Page: 1

Customer Order

(date format is: DD-MM-YY)

Print date
 14-02-25

Description
 Core-Bond B72 Regular

Lot number
Manufacture date
 07-05-24

Expiry date
 07-05-25

Comments

Result Description	Result	Units	Acceptance Range
Temperature	23.90	°C	>= 23.40 <= 24.40
Density	0.703	g/cm3	>= 0.680 <= 0.730
Viscosity (HAF, T-C, 5RPM)	108000	cP	>= 108000 <= 128000
Visc-Thix Index (1/10)	5.24	Units	>= 4.50 <= 6.50
Gel Time 100g + 2g DDM-9	55.0	Min	>= 50.0 <= 55.0
Peak Exotherm (100g)	306.8	°F	>= 0.0 <= 330.0
Time to peak	61.0	Min	>= 0.0 <= 80.0
Shore D hardness 24h Exterior (C 1/8 T)	68.00	Shord	>= 60.00 <= 80.00

Shelf Life : The material supplied is fit for purpose up until the expiry date, if stored as recommended

Storage conditions: Store between 2 and 23°C in the original, unopened container in a dry, well ventilated place. Protect from freezing and direct sunlight. Avoid contact with oxidising agents.

This document is processed electronically and carries no signature of approval.
 Quality department manager.